



RESIST TOP COAT



PRODUCT DESCRIPTION

RESIST TOP COAT is a blend of 100% methyl and methacrylate polymers used as a superior sealing and protective compound for wear surface aggregate. RESIST Top Coat brings out the wet look and highlights the natural pigments in the aggregate.

FEATURES:

- Coating dries clear and does not yellow with age or exposure to ultraviolet rays.
- Provides superior protection against freeze/thaw cycles, deicing salts, and chemical erosion and efflorescence.
- Reduces the possibility of aggregate pop-outs on exposed aggregate by percolating down and around the stones to fill gaps and voids.
- Forms a durable long-lasting film with resistance to water, chemicals, abrasion and stains.
- Highlights and preserves the natural pigments in the surface, adding longevity and sparkle to the finished product
- Does not discolor with over-use

USES:

Suitable for interior or exterior use on new or existing architectural concrete, burnish block, terrazzo, brick, stone, slate, quarry tile or other cementitious materials. Ideal for exposed aggregate, stamped/stenciled concrete, colored concrete surfaces, paving block, patio stone, driveways and garage floors. When used interior, solvent odor may linger. Extinguish all ignition sources and provide proper ventilation.

APPLICATION PROCEDURES

PREPARATION:

Surfaces must be clean, dry and free of form oils, grease, dust, frost and curing compounds (particularly wax based). Large areas may be blown dust free by compressed air, washed and let dry.

MIXING:

The material is ready for use and requires no mixing or dilution. It is unlawful to further dilute with non-exempt solvents.

APPLICATION:

RESIST Top Coat will darken concrete.

Apply using a low pressure (30-40lb) sprayer, roller or long nap applicator. Work the sealer into the surface avoiding accumulations, puddling, runs or sags. Because the material is fast drying, it should be applied in small sections while avoiding back rolling into drying areas.

FIRST AID:

- Consult this product's Safety Data Sheet for additional health and safety information. Safety Data Sheets are available through SureCrete & TK distributors, their offices, and the website.

AVAILABILITY:

RESIST TOP COAT is available through Surecrete and TK Products distributors. Visit www.surecretedesign.com for the nearest distributor.

Contact your Surecrete / TK Prodcuts representative for aggregate availability / recommendations

FOR PROFESSIONAL USE ONLY

COVERAGE:

SURFACE & COVERAGE

Exposed Aggregate 200-300 sq' per gallon

Textured/Stamped Concrete Surfaces 250-350 sq' per gallon

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

CLEAN UP:

Use TK-00 XYLENE to clean tools and equipment. Pump solvent through the sprayer to remove residue of materials which can clog the hose and wand assembly.

MAINTENANCE

Minimal maintenance is required other than occasional sweeping, dusting or mopping. If wear patterns do occur or if spillage removes the coating, RESIST TOP COAT may be reapplied to the affected area(s).

LIMITATIONS:

- Apply in temperatures above 40°F. Colder weather applications may be made under prescribed conditions and procedures specified by TK Products.
- Follow industry standards for use on colored concrete.
- Not for use on asphalt or surfaces subjected to hydrostatic water pressure, or as a waterproofer on below grade surfaces.
- Sprayers must be equipped with neoprene hose, washers and gaskets as rubber or other materials will disintegrate from the solvent.
- Product will freeze below 34°F. If frozen allow product to warm to 40°F and stir prior.

SUITABILITY SAMPLE

Always prepare a small mock-up area to test the compatibility of the coating with the prepared substrate. Mock up should be performed in an inconspicuous location and allowed to cure and dry fully. Inspect for proper film formation, gloss, and adhesion, and confirm that the film is free from whitening or any other defects.

NOTES:

*TK-00 XYLENE must be purchased separately

*Note 1. Concrete containing calcium chloride will remain dark longer when sealed. Ex-tenders and additives (concrete admixes, fly ash) are now being added to some ready mixed concrete which can cause inconsistency in the porosity of the concrete. Some areas of the finished concrete may then appear darker than others. To compensate for these variations, coverage ratios should be adjusted.

*Note 2. Pop-out problems can occur anytime, however, concrete in certain regional areas, concrete applied in extremely hot conditions (90°F+), and heavily steel troweled concrete can aggravate pop-out problems. These deficiencies are the result of a heat caused reaction, called alkaline silica reactivity (ASR), between the silica in the shale particles of the fine aggregate with the sodium and potassium alkali in the portland cement. For more information on this problem, refer to "POPOUTS" by Norman E. Henning, P.E. and Kenneth L. Johnson, P.E. of Twin City Testing and Engineering Laboratory and Lowery J. Smith of the J.L. Shiely Company. Where this type of shale is present, and extremely hot weather conditions prevail, it is recommended that liquid membrane curing compounds should not be used until the concrete has been completely cured by water ponding, continuous water spray mist, or wet burlap covering for a period of three days. A seal coat can then be applied for dust proofing and protection (when concrete is completely dry).

*Note 3. When using a liquid or powder release (other than TK-LIQUID STAMP RE-LEASE 2090) care must be taken to ensure proper washing has taken place prior to applying RESIST TOP COAT as these substances may affect product adhesion and formation.

COMPANION PRODUCTS:

RESIST SAND - Use RESIST sand per suggested coverage rates. If another sand is to be substituted, it must be approved by SureCrete. For Substitution request, please contact your SureCrete Account Manager or authorized reseller. Any sand that is not RESIST branded or approved will negate any product performance warranties.

- Broadcast to refusal on second coat of RESIST Epoxy 40- 50 sq' per bag.
- Provides a slip resistant surface with a broadcast layer of RESIST Sand.
- Engineered system that provides compatible products for addressing crack repair, surface defects as well as a no yellowing, color enhancing protective top coat.

RESIST Crack Repair - a two part system to effectively treat cracks in concrete or minimize their return inactive, structural cracks and patching concrete.

RESIST REPAIR MORTAR - Single component, high compressive strength, self-bonding, cement-based patching compound that sets up rapidly, with a 10-minute working time.

TECHNICAL DATA INFORMATION

Composition and Materials:	A copolymer blend in an exempt solvent solution
Percent Solid:	30%
Flash Point:	58° F
Drying Time:	Tack free: 1-2 hours Recoat: 2-4 hours Full Cure: 24 hours
VOC Content:	< 350 g/l
A.I.M. Category:	Concrete Curing Compounds
Maximum VOC:	350 g/l
Applicable Standards:	- ASTM C-1315, Type 1, Class A, B & C - ASTM C-309, Type 1, Class A & B and Type C, 1D with a red dye added. - Fed. TTC-C-800A, Type 1, Class 1 - AASHTO Des. M-148, Type 1, Clear - DE CRD - C-300 - USDA Authoriz tion for use in meat, poultry, and food processing plants. - esilient Tile Institute approval for compatibility with most resilient tile, carpet adhesives, and paints.